

Austrotherm EPS FASSADE®



IDEAL

THERMAL INSULATION

- ▶ **Ideal Insulation Performance**
 $\lambda: 0,034 \text{ W/mK}^*$
- ▶ **Ideal Application performance**
- ▶ **Ideal Cost**

* This value shows how much heat the material used transmits, and the low heat transmission coefficient indicates that the material has better heat insulation.

Austrotherm EPS FASSADE®

Thermal Insulation Board

Product sheet



Description

It is a gray colored thermal insulation board made of Expanded Polystyrene (EPS).

Properties:

It provides the ideal thermal insulation performance in EPS exterior insulation applications with its minimum 100kPa perpendicular tensile value and 0.033W/mK heat transmission coefficient value. It has enough flexibility, it does not break when cutting, does not spread and is easily applied to the wall. Dimensional stability and thermal insulation performance do not change during the life of the building. Gases harmful to human and environment are not used in its production.

Area of use:

It is used in exterior thermal insulation applications in buildings.

Storage Information:

It should be stored in a cool and ventilated, non-humid environment. Avoid contact with direct sunlight and being located near heat sources.

Quality certificates:

It complies with TS EN 13163: 2012 + A2 standard.



Technical Specifications

Product Type: EPS 50

Color: Gray

Thickness: Between 4cm - 10cm

Size: 50x100cm

Edge Shape: Straight

Cell Content: Air 98%, 2% Polystyrene

Packaging: PE nylon

Austrotherm EPS FASSADE®			
Technical Specifications	EPS 50	UNIT	CLASS
Thermal Conductivity Coefficient (λ)	0,034	W/mK	
Water Vapor Diffusion Resistance Factor - μ	20-40	μ	
Length Tolerance	± 2	mm	L2
Tolerance	± 2	mm	W2
Thickness Tolerance	± 1	mm	T1
Miter Tolerance	± 2	mm	S2
Surface Smoothness	± 3	mm	P3
Dimensional Stability in Fixed Conditions	$\pm 0,2$	%	DS(N)2
Dimensional Stability at Specific Temperature and Humidity	1	%	DS(70,-)1
Compressive Strength at 10% Deformation	≥ 50	kPa	CS(10)50
Crush Resistance	≥ 75	kPa	BS75
Tensile Strength Perpendicular to the Surface	≥ 100	kPa	TR 100
Long Term Water Absorption-Full Immersion	$\leq 0,5$	kg/m2	WL(7)0,5
Fire Resistance (TS EN 13501-1)	E		
Thickness*	4-10	cm	
Dimensions	50x100	cm	
Usage Temperatures	(-50/75(+))	°C	

* It is recommended to be used at least 4 cm and above thickness in external applications.

Austrotherm Yalıtım Malzemeleri San. Tic. Ltd. Şti. Sur Yapı Exen İstanbul, Tantavi Mah. Estergon Cad. F Blok, No: 24F, Kat: 39, Daire: 448, 34764 Ümraniye / İstanbul
Tel: +90 (216) 404 10 90 | Faks: +90 (216) 404 10 99 | info@austrotherm.com.tr | austrotherm.com.tr

Austrotherm Kocaeli Factory; Mermerciler San. Sit. Köşeler Köyü Mevki, 37.Cd. No:23, 41480 Dilovası / Kocaeli Tel: +90 (262) 728 14 40 Faks: +90 (262) 728 14 44

Austrotherm Manisa Factory; Selvili Tepe Mah. Tic. ve San. Odası Bul. No:1, 45400 OSB. Turgutlu / Manisa Tel: +90 (236) 314 14 38 Faks: +90 (236) 314 14 37

Austrotherm Ankara Factory; 1. OSB. Nahcivan Cad. No: 6, 6935 Sincan / Ankara Tel: +90 (312) 626 50 60

Austrotherm Kayseri Factory; İncesu OSB. Sultan Sazı 2. Cad. No:23, 38560 İncesu / Kayseri Tel: +90 (352) 502 08 38 Faks: +90 (352) 502 08 37

Austrotherm Trabzon Factory; Arsin OSB. 5. Cad. 61900 Arsin / Trabzon Tel: +90 (531) 783 73 88

Austrotherm Diyarbakır Factory; Elazığ Yolu Üzeri 22. Km. OSB. 2. Etap, 21100 Yenişehir / Diyarbakır Tel: +90 (545) 453 67 43